PROHLÁŠENÍ O VLASTNOSTECH

č. 0067 – CS

1. Jedinečný identifikační kód typu výrobku: **fischer injektážní systém FIS VL**

2. Zamýšlené/zamýšlená použití:

Výrobek	Zamýšlené/zamýšlená použití
Kovové injektážní kotvy pro montáž do zdiva	Kotvení, jejichž požadavky na bezpečnost a mechanickou odolnost a stabilitu musejí být splněny. Slouží pro upevnění a/nebo podporu konstrukčních prvků (které přispívají ke stabilitě konstrukcí) nebo těžkých dílců, viz. doplněk, obzvláště Přílohy B 1 - B 10

3. Výrobce: **fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Německo**

4. Zplnomocněný zástupce: **--**

5. Systém/systémy POSV: **1**

6a. Harmonizovaná norma: ---

Oznámený subjekt/oznámené subjekty: ---

6b. Evropský dokument pro posuzování: **ETAG 029; 2013-04**

Evropské technické posouzení: **ETA-15/0263; 2015-07-27**

Subjekt pro technické posuzování: **DIBt**

Oznámený subjekt/oznámené subjekty: **1343 – MPA Darmstadt**

7. Deklarovaná vlastnost/Deklarované vlastnosti:

Mechanická odolnost a stabilita (BWR 1)

Základní vlastnosti	Výkon
Charakteristická únosnost v tahu a ve smyku	Viz. doplněk, obzvláště Přílohy C 1 - C 4
Charakteristická únosnost pro ohybové momenty	Viz. dodatek, obzvláště Příloha C 5
Posuny při zatížení smykem a tahem	Viz. dodatek, obzvláště Příloha C 5
Redukční součinitel pro tahové zkoušky na stavbě (ß-Součinitel)	Viz. dodatek, obzvláště Příloha C 6
Vzdálenost k okraji a osová vzdálenost	Viz. doplněk, obzvláště Přílohy C 7 - C 8

Bezpečnost v případě požáru (BWR 2)

Základní vlastnosti	Výkon
Odolnost proti ohni	Kotvení splňuje požadavky Třídy A 1
Požární odolnost	Výkon není vypočten

8. Příslušná technická dokumentace a/nebo specifická technická dokumentace: ---

Vlastnosti výše uvedeného výrobku jsou ve shodě se souborem deklarovaných vlastností. Toto prohlášení o vlastnostech se v souladu s nařízením (EU) č. 305/2011 vydává na výhradní odpovědnost výrobce uvedeného výše.

Podepsáno za výrobce a jeho jménem:

Andreas Bucher, Dipl.-Ing. Wolfgang Hengesbach, Dipl.-Ing., Dipl.-Wirtsch.-Ing.

Tumlingen, 2015-08-12

- Toto PoV bylo připraveno v různých jazykových mutacích.. V případě rozporu vždy rozhoduje interpretace verze v anglickém jazyce.
- Příloha obsahuje nepovinné a doplňkové informace v anglickém jazyce na rámec zákonných požadavků.

Specific Part

1 Technical description of the product

The fischer injectionsystem FIS VL for masonry is a bonded anchor (injection type) consisting of a mortar cartridge with injection mortar fischer FIS VL, FIS VL Low Speed and FIS VL High Speed, a perforated sieve sleeve and an anchor rod with hexagon nut and washer or an internal threaded rod. The steel elements are made of zinc coated steel, stainless steel or high corrosion resistant steel.

The anchor rod is placed into a drilled hole filled with injection mortar and is anchored via the bond between steel element, injection mortar and masonry and mechanical interlock.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance for tension and shear loads	See Annex C 1 – C 4
Characteristic resistance for bending moments	See Annex C 5
Displacements under shear and tension loads	See Annex C 5
Reduction Factor for job site tests (β-Factor)	See Annex C 6
Edge distances and spacing	See Annex C 7 – C8

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorages satisfy requirements for Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.


4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with guideline for European technical approval ETAG 029, April 2013 used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011 the applicable European legal act is: [97/177/EC].

The system to be applied is: 1

Installation conditions part 1


Threaded rods with perforated sleeve FIS H K; Installation in perforated and solid brick masonry



Pre-positioned installation

FIS H 12x85 K
FIS H 16x85 K
FIS H 16x130 K
FIS H 20x85 K
FIS H 20x130 K
FIS H 20x200 K

Internal threaded anchors FIS E with perforated sleeve FIS H K; Installation in perforated and solid brick masonry



Pre-positioned installation

FIS H 16x85 K – FIS E 11x85 M6 and M8
FIS H 20x85 K – FIS E 15x85 M10 and M12

h_{ef} = effective anchorage depth
h_0 = depth of drill hole
t_{fix} = thickness of fixture
h = thickness of masonry


d_0 = nominal drill bit diameter
d_f = diameter of clearance hole in the fixture
$T_{inst,max}$ = maximum torque moment

fischer Injectionsystem FIS VL for masonry	**Annex A 1**
Product description Installation condition, part 1: in perforated and solid brick masonry	


Installation conditions part 2

Threaded rods without perforated sleeve FIS H K; Installation in solid brick masonry and autoclaved aerated concrete

Pre-positioned installation




Push through installation



Annular gap filled with mortar

Internal threaded anchors FIS E without perforated sleeve FIS H K; Installation in solid brick masonry and autoclaved aerated concrete




Pre-positioned installation

FIS E 11x85 M6
FIS E 11x85 M8
FIS E 15x85 M10
FIS E 15x85 M12

h_{ef} = effective anchorage depth
h_0 = depth of drill hole
t_{fix} = thickness of fixture
h = thickness of masonry

d_0 = nominal drill bit diameter
d_f = diameter of clearance hole in the fixture
$T_{inst,max}$ = maximum torque moment

fischer Injectionsystem FIS VL for masonry	**Annex A 2**
Product description Installation condition, part 2: in solid brick masonry and autoclaved aerated concrete	



1.	**Mortar cartridge**	4.	**Hexagon nut**
2.	**Threaded rod**	5.	**Internal threaded anchor FIS E**
3.	**Washer**	6.	**Perforated sleeve FIS H K**

fischer Injectionsystem FIS VL for masonry	**Annex A 3**
Product description Cartridges, anchor rods, internal threaded anchors, perforated sleeves	

Table A1: Materials

Part	Designation	Material		
1	Mortar cartridge	mortar, hardener; filler		
		Steel, zinc plated	Stainless steel A4	High corrosion-resistant steel C
2	Threaded rod	Property class 5.8 or 8.8; ISO 898-1:2013 zinc plated ≥ 5µm, EN ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004 $f_{uk} \leq 1000$ N/mm² $A_5 > 8\%$	Property class 50, 70 or 80 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062 EN 10088-1:2014 $f_{uk} \leq 1000$ N/mm² $A_5 > 8\%$	Property class 50 or 80 EN ISO 3506:2009 or property class 70 with f_{yk}= 560 N/mm² 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000$ N/mm² $A_5 > 8\%$
3	Washer ISO 7089:2000	zinc plated ≥ 5µm, EN ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004	1.4401; 1.4404; 1.4578;1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565;1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 5 or 8; ISO 898-2:2013 zinc plated ≥ 5µm, ISO 4042:1999 A2K or hot-dip galvanised ISO 10684:2004	Property class 50, 70 or 80 ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 ISO 3506:2009 1.4565; 1.4529 EN 10088-1:2014
5	Internal threaded anchor FIS E	Property class 5.8; EN 10277-1:2008-06 zinc plated ≥ 5µm, EN ISO 4042:1999 A2K	Property class 70 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
	Screw or threaded rod for internal threaded anchor FIS E	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated ≥ 5µm, ISO 4042:1999 A2K	Property class 70 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
6	Perforated sleeve FIS H K	PP / PE		

Specifications of intended use

Anchorages subject to:

- Static and quasi-static loads

Base materials:

- Solid brick masonry (Use category b) and autoclaved aerated concrete (Use category d), acc. to Annex B8.
  Note: The characteristic resistance is also valid for larger brick sizes and higher compressive strength of the masonry unit.
- Hollow brick masonry (use category c), according to Annex B8
- Mortar strength class of the masonry M2,5 at minimum according to EN 998-2:2010
- For other bricks in solid masonry, hollow or perforated masonry and autoclaved aerated concrete, the characteristic resistance of the anchor may be determined by job site tests according to ETAG 029, Annex B under consideration of the β-factor according to Annex C6, Table C4

Temperature Range:

- **I**: From - 40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)

Use conditions (Environmental conditions):

- Dry and wet structure (regarding injection mortar)
- Structures subject to dry internal conditions exist
  (zinc coated steel, stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure including industrial and marine environment or exposure to permanently damp internal condition, if no particular aggressive conditions exist
  (stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (high corrosion resistant steel)
  Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used)

fischer Injectionsystem FIS VL for masonry	**Annex B 1**
Intended Use Specifications	

Specifications of intended use

Design:

- The anchorages have to be designed in accordance with the ETAG 029, Annex C, Design method A under the responsibility of an engineer experienced in anchorages and masonry work
  Applies to all bricks, if no other values are specified:

  $N_{Rk} = N_{Rk,s} = N_{Rk,p} = N_{Rk,b} = N_{Rk,pb}$

  $V_{Rk} = V_{Rk,s} = V_{Rk,b} = V_{Rk,c} = V_{Rk,pb}$

- Verifiable calculation notes and drawings have to be prepared taking account the relevant masonry in the region of the anchorage, the loads to be transmitted and their transmission to the supports of the structure. The position of the anchor is indicated on the design drawings

Installation:


- Category d/d: -Installation and use in dry structures
- Category w/w: -Installation and use in dry and wet structures
- Hole drilling by hammer drill mode
- In case of aborted hole: The hole shall be filled with mortar
- Bridging of unbearing layer (e.g. plaster) see Annex B 4 (Table B1.3)
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- Fastening screws or threaded rods (including nut and washer) must comply with the appropriate material and property class of the fischer internal threaded anchor FIS E
- minimum curing time see Annex B5. Table B3
- Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:

  Material dimensions and mechanical properties of the metal parts according to the specifications are given in Annex A4, Table A1

  Conformation of material and mechanical properties of the metal parts by inspection certificate 3.1 according to EN 10204:2004, the documents shall be stored

  Marking of the threaded rod with the envisage embedment depth. This may be done by the manufacturer of the rod or by a person on job site

fischer Injectionsystem FIS VL for masonry	**Annex B 2**
Intended Use Specifications	




Marking:
Property class 8.8 or high corrosion-resistant steel C, property class 80: •
Stainless steel A4, property class 50 and high corrosion-resistant steel C, property class 50: ••

Table B1.1: Installation parameters for threaded rod without perforated sleeve

Size				M8	M10	M12
Nominal drill hole diameter		$d_{nom}=d_0$	[mm]	10	12	14
Width across flat		SW	[mm]	13	17	19
Effective anchorage depth[1]		$h_{ef,min}$	[mm]	50		
Depth of drill hole $h_0 = h_{ef}$		$h_{ef,max}$	[mm]	h-30 and ≤ 200 mm		
Effective anchorage depth AAC		$h_{ef,min}$	mm]	100		
		$h_{ef,max}$	[mm]	120		
Maximum torque moment		$T_{inst,max}$	[Nm]	10		
Max. torque moment for autoclaved aerated concrete		$T_{inst,max}$	[Nm]	1	2	
Diameter of clearance hole in the fixture	Pre-position anchorage	$d_f \leq$	[mm]	9	12	14
	Push through anchorage	$d_f \leq$	[mm]	11	14	16

[1] $h_{ef,min} \leq h_{ef} \leq h_{ef,max}$ is possible.

fischer internal threaded anchor FIS E



Marking: size, e.g. M8
stainless steel A4: e.g. M8 A4
high corrosion-resistant steel C: e.g. M8 C

Table B1.2: Installation parameters for internal threaded anchor FIS E without perforated sleeve

Size FIS E			11x85 M6	11x85 M8	15x85 M10	15x85 M12
diameter of internal threaded anchor	d_H	[mm]	11		15	
Nominal drill hole diameter	$d_{nom}=d_0$	[mm]	14		18	
Depth of drill hole	h_0	[mm]	85			
Effective anchorage depth	$L_H=h_{ef}$	[mm]	85			
Maximum torque moment	$T_{inst,max}$	[Nm]	4	10		
Max. torque moment for autoclaved aerated concrete	$T_{inst,max}$	[Nm]	1		2	
Diameter of clearance hole in the fixture	$d_f \leq$	[mm]	7	9	12	14
Screw-in depth	$L_{E,min}$	[mm]	6	8	10	12

fischer Injectionsystem FIS VL for masonry

Intended Use
Installation parameters, part 1

Annex B 3

Perforated sleeves FIS H 12x85; 16x85; 16x130; 20x85; 20x130; 20x200 K

Marking:size
D_{Sleeve} x L_{Sleeve}
e.g. 16x85







Table B1.3: Installation parameters (threaded rod and internal threaded anchor with perforated sleeve; only pre-positioned anchorage)

Size FIS H…K			12x85	16x85	16x130[2)]	20x85	20x130[2)]	20x200[2)]
Nominal drill hole diameter ($d_0 = D_{Sleeve}$)	$d_{nom}=d_0$	[mm]	12	16		20		
Depth of drill hole	h_0	[mm]	90	90	135	90	135	205
Effective anchorage depth[1)]	$h_{ef,min}$	[mm]	85	85	110	85	110	180
	$h_{ef,max}$	[mm]	85	85	130	85	130	200
Size of threaded rod		[-]	M8	M8, M10		M12		
Size of internal threaded anchor		[-]	----	11x85	----	15x85	----	----
Maximum torque moment threaded rod and internal threaded anchor	$T_{inst,max}$	[mm]	2					

[1)] $h_{ef,min} \le h_{ef} \le h_{ef,max}$ is possible.
[2)] Bridging of unbearing layer (e.g. plaster) possible

Steel brush BS



Only for solid bricks and autoclaved aerated concrete

Table B2: Parameters of steel brush

Drill hole diameter	d_0	[mm]	10	12	14	16	18	20
Brush diameter	$d_{b,nom}$	[mm]	11	14	16	20	20	25

Table B3: Maximum processing time of the mortar and minimum curing time

(During the curing time of the mortar the masonry temperature may not fall below the listed minimum temperature).







Temperature at anchoring base [°C]	Minimum curing time [1] t_{cure} [minutes]		
	FIS VL High Speed[3]	FIS VL[2]	FIS VL Low Speed[2]
-10 to -5	12 hours		
>-5 to ±0	3 hours	24 hours	
>±0 to +5	90	3 hours	6 hours
>+5 to +10	45	90	3 hours
>+10 to +20	30	60	2 hours
>+20 to +30		45	60
>+30 to +40		35	30

System-temperature (mortar) [°C]	Maximum processing time t_{work} [minutes]		
	FIS VL High Speed	FIS VL[2]	FIS VL Low Speed[2]
±0	5		
+5	5	13	20
+10	3	9	20
+20	1	5	10
+30		4	6
+40		2	4

[1] For wet bricks the curing time must be doubled
[2] Minimum cartridge temperature +5°C
[3] Minimum cartridge temperature ±0°C

Installation instructions Part 1

Installation and Preparing the cartridge in solid brick and autoclaved aerated concrete (without perforated sleeve)






1		Drill the hole. Depth of drill hole h_0 and drill hole diameter d_0 see Table **B1.1** or **B1.2**
2		Blow out the drill hole two times. Brush the drill hole two times (see Table B2) and blow out two times again
3		Remove the sealing cap Screw on the static mixer (the spiral in the static mixer must be clearly visible)
4		Place the cartridge into a suitable dispenser. Press out approximately 10 cm of material until the mortar is permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed off.
5		Fill approximately 2/3 of the drill hole with mortar Always begin from the bottom of the hole to eliminate voids[1]. For push through installation (not FIS E) fill the annular gap also with mortar.
6		Only use clean and oil-free anchor elements. Mark the threaded rod for setting depth. Press the threaded rod or internal threaded anchor FIS E down to the bottom of the hole, turning it slightly by hand while doing. After inserting the anchor element, excess mortar must emerge around the anchor element.
7		Do not touch. Minimum curing time t_{cure} see Table **B3** Mounting the fixture $T_{inst,max}$ see Table **B1.1** or **B1.2**

[1] For the exact quantity of mortar see manufacturer`s specification.

fischer Injectionsystem FIS VL for masonry	**Annex B 6**
Intended Use Installation instructions part 1 in solid brick and autoclaved aerated concrete	

















Installation instructions Part 2

Installation in perforated or solid brick with perforated sleeve (pre-positioned anchorage)

1		Drill the hole (hammer drill). Depth of drill hole h_0 and drill hole diameter d_0 see Table **B1.3**	When install perforated sleeves in solid bricks or solid areas of hollow bricks, also clean the hole by blowing out and brushing	
2		Remove the sealing cap		Screw on the static mixer (the spiral in the static mixer must be clearly visible)
3		Place the cartridge into a suitable dispenser		Press out approximately 10 cm of material until the mortar is permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed off
4		Insert the perforated sleeve flush with the surface of the masonry or plaster .		Fill the perforated sleeve completely with mortar beginning from the bottom of the hole[1)].
5			Only use clean and oil-free anchor elements. Mark the threaded rod for setting depth. Insert the threaded rod or the internal threaded anchor FIS E by hand using light turning motions until reaching the setting depth marking (threaded rod) or flush with the surface (internal threaded anchor).	
6		Do not touch. Minimum curing time t_{cure} see Table **B3**		Mounting the fixture. $T_{inst,max}$ see Table B1.3

[1)] For the exact quantity of mortar see manufacturer`s specification.













Table B 4: Summary of bricks and blocks

Brick No. 1 Solid brick Mz according to EN 771-2 $\rho \geq 1{,}8$ [kg/dm^3] fb ≥ 10 or 20 [N/mm^2]			**Brick No. 6** Perforated brick HLz according to EN 771-1 $\rho \geq 1{,}4$ [kg/dm^3] fb ≥ 20 [N/mm^2]		
Brick No. 2 Solid sand-lime brick according to EN 771-2 $\rho \geq 1{,}8$ [kg/dm^3] fb ≥ 10 or 20 [N/mm^2]			**Brick No. 7** Perforated brick HLz according to EN 771-1 $\rho \geq 1{,}0$ [kg/dm^3] fb ≥ 10 [N/mm^2]		
Brick No. 3 Solid sand-lime brick according to EN 771-2 $\rho \geq 1{,}8$ [kg/dm^3] fb ≥ 10 or 20 [N/mm^2]			**Brick No. 8** Perforated brick HLz filled with mineral wool according to EN 771-1 $\rho \geq 0{,}6$ [kg/dm^3] fb ≥ 8 [N/mm^2]		
Brick No. 4 Sand-lime hollow brick according to EN 771-2 $\rho \geq 1{,}4$ [kg/dm^3] fb ≥ 12 or 20 [N/mm^2]			**Brick-No. 9** Light-weight concrete hollow block **Hbl** according to EN 771-1 $\rho \geq 1{,}0$ [kg/dm^3] fb ≥ 4 [N/mm^2]		
Brick No. 5 Perforated brick HLz according to EN 771-1 $\rho \geq 0{,}9$ [kg/dm^3] fb ≥ 10 [N/mm^2]			**Brick No. 10** Autoclaved aerated concrete block $\rho \geq 350$, 500 or 650 [kg/dm^3] fb ≥ 2, 4 or 6 [N/mm^2]		

Imaging of the bricks are not scaled

fischer Injectionsystem FIS VL for masonry	**Annex B 8**
Intended Use Types and dimensions of blocks and bricks	

Table B5.1: Allocation of anchor rods[1], perforated sleeves[1)2)] and perforated or solid bricks








Kind of masonry	Brick	Valid anchor rods, internal threaded rods and perforated sleeves	
Brick No. 1 Solid brick Mz according to EN 771-2 $\rho \geq 1{,}8$ [kg/dm^3] fb ≥ 10 or 20 [N/mm^2]			M8; M10; M12 FIS E 11x85
Brick No. 2 Solid sand-lime brick according to EN 771-2 $\rho \geq 1{,}8$ [kg/dm^3] fb ≥ 10 or 20 [N/mm^2]			M8; M10; M12 FIS E 11x85
Brick No. 3 Solid sand-lime brick according to EN 771-2 $\rho \geq 1{,}8$ [kg/dm^3] fb ≥ 10 or 20 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K FIS H 16x130 K FIS H 20x130 K
Brick No. 4 Sand-lime hollow brick according to EN 771-2 $\rho \geq 1{,}4$ [kg/dm^3] fb ≥ 12 or 20 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K FIS H 16x130 K FIS H 20x130 K
Brick No. 5 Perforated brick HLz according to EN 771-1 $\rho \geq 0{,}9$ [kg/dm^3] fb ≥ 10 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K FIS H 16x130 K FIS H 20x130 K
Brick No. 6 Perforated brick HLz according to EN 771-1 $\rho \geq 1{,}4$ [kg/dm^3] fb ≥ 20 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K

[1)] Other combinations can be used after job site tests acc. to ETAG 029, Annex B.
[2)] Sleeve/anchor rod combination see table B1.3

The β- factor for this job site tests are given in Table C4
Imaging of the bricks are not scaled

fischer Injectionsystem FIS VL for masonry	**Annex B 9**
Intended Use Allocation of anchor rods, perforated sleeves and bricks, part 1	

Table B5.2: Allocation of anchor rods[1], perforated sleeves[1)2)] and perforated or solid bricks

Kind of masonry	Brick	Valid anchor rods internal threaded rods and perforated sleeves	
Brick No. 7 Perforated brick HLz according to EN 771-1 $\rho \geq 1{,}0$ [kg/dm^3] fb ≥ 10 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K FIS H 20x130 K
Brick No. 8 Perforated brick HLz filled with mineral wool according to EN 771-1 $\rho \geq 0{,}6$ [kg/dm^3] fb ≥ 8 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K FIS H 16x130 K FIS H 20x130 K FIS H 20x200 K
Brick-No. 9 Light-weight concrete hollow block Hbl according to EN 771-1 $\rho \geq 1{,}0$ [kg/dm^3] fb ≥ 4 [N/mm^2]			FIS H 12x85 K FIS H 16x85 K FIS H 20x85 K FIS H 16x130 K FIS H 20x130 K
Brick No. 10 Autoclaved aerated concrete block $\rho \geq 350$, 500 or 650 [kg/dm^3] fb ≥ 2, 4 or 6 [N/mm^2]			M8; M10; M12 FIS E 11x85 M6 FIS E 11x85 M8 FIS E 15x85 M10 FIS E 15x85 M12



[1)] Other combinations can be used after job site tests acc. to ETAG 029, Annex B.
[2)] Sleeve/anchor rod combination see table B1.3

The β- factor for this job site tests are given in Table C4

Imaging of the bricks are not scaled



fischer Injectionsystem FIS VL for masonry	**Annex B 10**
Intended Use Allocation of anchor rods, perforated sleeves and bricks, part 2	

Table C1.1: Characteristic values of resistance under tension loads and under shear loads

Brick	Density ρ [kg/dm³] - Compressive strength f_b [N/mm²]	Perforated sleeve FIS H…K	Anchor size or screw size in internal threaded anchor	Effective anchorage depth		Characteristic resistance [kN]		
						N_{Rk}		V_{Rk}
						Temp. 50/80°C		All categories
				$h_{ef,min}$ [mm]	$h_{ef,max}$ [mm]	d/d	w/w	
 **No.1** Solid brick Mz	ρ ≥ 1,8 f_b ≥ 10	without	M8	50	200	4,0	2,5	2,5
			M10	50	79	3,5	2,0	4,0
			M10	80	199	5,0	3,0	
			M10	200	200	8,5	7,5	8,5
			M12	50	79	3,0	2,0	4,0
			M12	80	199	5,5	3,5	
			M12	200	200	8,0	5,0	8,5
			FIS E11x85 M6/ M8,	85	85	5,5	3,5	2,5
	ρ ≥ 1,8 f_b ≥ 20		M8	50	200	5,5	3,5	4,0
			M10	50	79	5,0	3,0	6,0
			M10	80	199	7,0	4,5	
			M10	200	200	8,5	8,5	8,5
			M12	50	79	4,5	3,0	5,5
			M12	80	199	8,0	5,0	
			M12	200	200	8,5	7,0	8,5
			FIS E11x85 M6/ M8,	85	85	8,0	5,0	4,0
 **No.2** Solid sand-lime brick	ρ ≥ 1,8 f_b ≥ 10	without	M8	50	200	2,5	1,5	4,0
			M10	50	79			
			M10	80	199			
			M10	200	200	8,5	6,0	
			M12	50	79	2,5	1,5	5,0
			M12	80	199			
			M12	200	200	8,5	6,5	
			FIS E11x85 M6/ M8,	85	85	2,5	1,5	3,0
	ρ ≥ 1,8 f_b ≥ 20		M8	50	200	3,5	2,0	5,5
			M10	50	79			
			M10	80	199			
			M10	200	200	8,5	8,5	
			M12	50	79	3,5	2,0	7,0
			M12	80	199			
			M12	200	200	8,5	8,5	
			FIS E11x85 M6/ M8,	85	85	3,5	2,0	4,0






Imaging of the bricks are not scaled

Table C1.2: Characteristic values of resistance under tension loads and under shear loads

Brick	Density ρ [kg/dm³] - Compressive strength f_b [N/mm²]	Perforated sleeve FIS H…K	Anchor size or screw size in internal threaded anchor	Effective anchorage depth		Characteristic resistance [kN]		
						N_{Rk}		V_{Rk}
						Temp. 50/80°C		All categories
				$h_{ef,min}$ [mm]	$h_{ef,max}$ [mm]	d/d	w/w	
 **No.3** Solid sand-lime brick	ρ ≥ 1,8 f_b ≥ 10	12x85	M8	85	85	6,0	3,5	3,0
		16x85	FIS E 11x85 M6	85	85	3,5	2,0	
		16x85	M8/M10, FIS E 11x85 M8	85	85	3,5	2,0	3,5
		20x85	M12, FIS E 15x85	85	85	8,5	6,5	
		16x130	M8/M10	110	130	3,5	2,0	
		20x130	M12	110	130	7,0	4,5	
	ρ ≥ 1,8 f_b ≥ 20	12x85	M8	85	85	8,5	5,0	4,5
		16x85	FIS E 11x85 M6	85	85	5,5	3,0	
		16x85	M8/M10, FIS E 11x85 M8	85	85	5,5	3,0	5,5
		20x85	M12, FIS E 15x85	85	85	8,5	8,5	
		16x130	M8/M10	110	130	5,0	3,0	
		20x130	M12	110	130	8,5	6,0	
 **No.4** Sand-lime hollow brick	ρ ≥ 1,4 f_b ≥ 12	12x85	M8	85	85	2,5	2,5	2,5
		16x85	FIS E 11x85 M6	85	85	3,0	2,5	
		16x85	M8/M10, FIS E 11x85 M8	85	85	3,0	2,5	4,5
		20x85	M12, FIS E 15x85	85	85	3,5	3,0	4,5
		16x130	M8/M10	110	130			
		20x130	M12	110	130			
	ρ ≥ 1,4 f_b ≥ 20	12x85	M8	85	85	4,5	4,0	4,5
		16x85	FIS E 11x85 M6	85	85	5,0	4,0	4,0
		16x85	M8/M10, FIS E 11x85 M8	85	85	5,0	4,5	7,5
		20x85	M12, FIS E 15x85	85	85	6,0	5,5	7,5
		16x130	M8/M10	110	130			
		20x130	M12	110	130			

Imaging of the bricks are not scaled


Table C1.3: Characteristic values of resistance under tension loads and under shear loads

Brick	Density ρ [kg/dm³] - Compressive strength f_b [N/mm²]	Perforated sleeve FIS H…K	Anchor size or screw size in internal threaded anchor	Effective anchorage depth		Characteristic resistance [kN]		
						N_{Rk}		V_{Rk}
						Temp. 50/80°C		All categories
				$h_{ef,min}$ [mm]	$h_{ef,max}$ [mm]	d/d	w/w	
 **No.5** Perforated brick HLz	ρ ≥ 0,9 f_b ≥ 10	12x85	M8	85	85	4,0	3,5	4,0
		16x85	FIS E 11x85 M6	85	85	3,5	3,5	4,0
		16x85	M8/M10, FIS E 11x85 M8	85	85	3,5	3,5	5,5
		20x85	M12, FIS E 15x85	85	85	5,0	4,5	6,0
		16x130	M8/M10	110	130	5,0	4,5	5,5
		20x130	M12	110	130	5,0	4,5	6,0
 **No.6** Perforated brick HLz	ρ ≥ 1,4 f_b ≥ 20	12x85	M8	85	85	4,0	3,5	7,5 (5,5)[1]
		16x85	FIS E 11x85 M6	85	85	2,5		4,0
		16x85	M8/M10, FIS E 11x85 M8	85	85	2,5		4,5
		20x85	M12, FIS E 15x85	85	85	3,0		8,5 (5,5)[1]
 **No.7** Perforated brick HLz	ρ ≥ 1,0 f_b ≥ 10	12x85	M8	85	85	0,9		1,2
		16x85	M8/M10, FIS E 11x85	85	85	2,5		
		20x85	M12, FIS E 15x85	85	85			
		16x130	M8/M10	110	130			1,5
		20x130	M12	110	130	3,5	3,0	1,5
 **No.8** Perforated brick HLz	ρ ≥ 0,6 f_b ≥ 8	12x85	M8	85	85	2,0	2,0	2,5
		16x85	FIS E 11x85 M6	85	85	2,0	1,5	2,5
		16x85	M8/M10, FIS E 11x85 M8	85	85	2,0	1,5	3,0
		20x85	M12. FIS E 15x85	85	85	2.0	2.0	1.5
		16x130	M8/M10	130	130	3,0	2,5	3,0
		20x130	M12	110	130	2,0	2,0	1,5
		20x200	M12	180	200	3,0	3,0	1,5
 **No.9** Light-weight concrete hollow block	ρ ≥ 1,0 f_b ≥ 4	12x85	M8	85	85	3,0		2,0
		16x85	M8/M10, FIS E 11x85	85	85			
		20x85	M12, FIS E 15x85	85	85			
		16x130	M8/M10	110	130			
		20x130	M12	110	130			

[1] Characteristic value of pushing out of one brick $V_{Rk,pb}$ = 5,5 kN

Imaging of the bricks are not scaled

Table C1.4: Characteristic values of resistance under tension loads and under shear loads

Brick	Density ρ [kg/dm³] - Compressive strength f_b [N/mm²]	Perforated sleeve FIS H…K	Anchor size or screw size in internal threaded anchor	Effective anchorage depth		Characteristic resistance [kN]		
						N_{Rk}		V_{Rk}
						Temp. 50/80°C		All categories
				$h_{ef,min}$ [mm]	$h_{ef,max}$ [mm]	d/d	w/w	
 **No.10** Autoclaved Aerated concrete block	ρ ≥ 350 f_b ≥ 2	ohne	M8	100	120	1,5		1,2
			M10	100	120			1,2
			M12	100	120			1,5
			FIS E 11x85 FIS E 15x85	85				1,2
	ρ ≥ 500 f_b ≥ 4	ohne	M8	100	120	2,0		2,5
			M10	100	120	2,5		2,0
			M12	100	120			2,5
			FIS E 11x85 FIS E 15x85	85		2,0		2,0
	ρ ≥ 650 f_b ≥ 6	ohne	M8	100	120	3,5	3,0	3,0
			M10	100	120	5,0	4,5	3,0
			M12	100	120			3,5
			FIS E 11x85 FIS E 15x85	85		3,5		2,5

Imaging of the bricks are not scaled

Table C2: Characteristic bending moments for threaded rods

Größe				M8	M10	M12
Characteristic bending moment $M_{Rk,s}$	Zinc-plated steel	Property class	5.8 [Nm]	19	37	65
			8.8 [Nm]	30	60	105
	Stainless steel A4	Property class	50 [Nm]	19	37	65
			70 [Nm]	26	52	92
			80[Nm]	30	60	105
	High corrosion-resistant steel C	Property class	50 [Nm]	19	37	65
			70[1)] [Nm]	26	52	92
			80 [Nm]	30	60	105

[1)] f_{uk}= 700 N/mm^2; f_{yk}=560 N/mm^2

Table C2.1: Characteristic bending moments for internal threaded anchors FIS E

Size FIS E				11x85 M6	11x85 M8	15x85 M10	15x85 M12
Characteristic bending moments $M_{Rk,s}$	zinc plated steel,	Property class of screw	5.8 [Nm]	8	19	37	65
			8.8 [Nm]	12	30	60	105
	stainless steel A4	Property class of screw	70 [Nm]	11	26	52	92
	high corrosion resistant steel C	Property class of screw	70 [Nm]	11	26	52	92

Tabelle C3: Displacements under tension loads and shear loads

Material	N [kN]	δN_0 [mm]	δN_∞ [mm]	V [kN]	δV_0 [mm]	δV_∞ [mm]
solid units and autoclaved aerated concrete	$\frac{N_{Rk}}{1,4 * \gamma_M}$	0,03	0,06	$\frac{V_{Rk}}{1,4 * \gamma_M}$	0,59	0,88
hollow units	$\frac{N_{Rk}}{1,4 * \gamma_M}$	0,03	0,06	$\frac{V_{Rk}}{1,4 * \gamma_M}$	1,71	2,56


Table C4: β- factor for job site tests according to ETAG 029, Annex B

Using categories		w/w	d/d
Temperature range [°C]		50/80	50/80
Brick	Size[1)]		
Solid brick	M8	0,57	0,96
	M10	0,59	
	M12 FIS E 11x85 FIS E 15x85	0,60	
Hollow brick	All sizes	0,86	0,96
Autoclaved aerated concrete	All size	0,73	0,81

Table C5: Edge distance and spacing

Direction to bed joint			⊥		∥		Group factor				Min. thickness of the masonry members
Brick No.	h_{ef} [mm]	$c_{cr} = c_{min}$	s_{min}	s_{cr}	s_{min}	s_{cr}	⊥		∥		
		[mm]	[mm]	[mm]	[mm]	[mm]	$\alpha_{g,N}$	$\alpha_{g,V}$	$\alpha_{g,N}$	$\alpha_{g,V}$	[mm]
1	50	100	75		60[1]	150	2	2	1,5	1,4	h_{ef} + 30 (≥ 80)
	80	100	75		60[1]	240	2	2	1,5	1,4	
	200	150	75		240		2				
2	50	100	75		240		2				
	80	100	75		240		2				
	200	150	75		240		2				
3	85	100	115		240		2				
	130	100	115		240		2				
4	all sizes	100	115		100	240	2	2	1,5	1,5	
5	all sizes	100	115		240		2				
6	all sizes	100	115		240		2				
7	all sizes	100	100	240	100	375 (500)[2]	1	1	1	1	
8	all sizes	120	245		250		2				
9	all sizes	80	240		365		2				
10	all sizes	100	250		300		2				

[1] only valid for tension loads, for shear loads $s_{min}\| = s_{cr}\|$
[2] spacing depending on brick dimension, brick dimension see table B4, brick 7



* Only, if joints are visible and
vertical joints are not filled with mortar

s_{min} || = Minimum spacing parallel to bed joint
$s_{min}^{\perp}$ = Minimum spacing vertical to bed joint
s_{cr} || = Characteristic spacing parallel to bed joint
$s_{cr}^{\perp}$ = Characteristic spacing vertical to bed joint
$c_{cr} = c_{min}$ = Edge distance
$\alpha_{g,N}$ || = Group factor for tension load parallel to bed joint
$\alpha_{g,V}$ || = Group factor for shear load parallel to bed joint
$\alpha_{g,N}^{\perp}$ = Group factor for tension load vertical to bed joint
$\alpha_{g,V}^{\perp}$ = Group factor for shear load vertical to bed joint

For $s > s_{cr}$ $\alpha_g = 2$

For $s_{min} \leq s \leq s_{cr}$ α_g according to table C5

$N^g_{Rk} = \alpha_{g,N} \cdot N_{Rk}$; $V^g_{Rk} = \alpha_{g,V} \cdot V_{Rk}$ (Group of 2 anchors)

$N^g_{Rk} = \alpha_{g,N}\,\| \cdot \alpha_{g,N}^{\perp} \cdot N_{Rk;}$ $V^g_{Rk} = \alpha_{g,V}\,\| \cdot \alpha_{g,V}^{\perp} \cdot V_{Rk}$ (Group of 4 anchors)

fischer Injectionsystem FIS VL for masonry	**Annex C 8**
Performances Definition of minimum edge distance, minimum spacing and group factors	